



# Thermafiber® FireSpan™ 40 & 90 Mineral Wool Fire Containment Insulation

## PRODUCT FEATURES

### Description

Mineral wool insulation designed to provide enhanced fire protection in curtain wall and perimeter fire containment systems, with thermal and acoustical properties.

### Basic Uses/Related Uses

Fire protection insulation for curtain wall and perimeter fire containment systems. Tested systems include:

- Aluminum-Framed/Aluminum Spandrel Perimeter Fire Barrier
- Steel Stud-Framed/Gypsum Sheathing Perimeter Fire Barrier
- Aluminum-Framed/Glass Spandrel Perimeter Fire Barrier
- Aluminum-Framed/Granite Spandrel Perimeter Fire Barrier
- Precast Concrete Spandrel

### Selection Criteria

- Independently tested for use in perimeter fire containment assemblies having 1, 2 and 3 hour fire resistance ratings
- Non-combustible
- Moisture resistant and non-deteriorating
- Non-corrosive
- Vermin resistant
- Optional vapour retarding foil facing for use in applicable construction assemblies
- Helps conserve energy, reduce greenhouse gas emissions
- Fire resistant to temperatures above 1,093° C (2,000° F)
- Enhances acoustical performance
- Natural dark color provides shadowing in glass spandrels

### Sustainability Criteria

- Recycled content minimum 70%, standard fiber
- Bronze Material Health Certificate from Cradle to Cradle
- Contributes to credits in several green building programs such as LEED® and Green Globes®
- For more information see Environmental Product Declaration (EPD) certified by UL Environment via [www.thermafiber.ca/sustainability](http://www.thermafiber.ca/sustainability)

## Applicable Standards

<b>CAN/ULC-S702</b>	Standard for Mineral Fibre Thermal Insulation for Buildings
<b>ASTM C665</b>	Standard Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing
<b>ASTM C612</b>	Standard Specification for Mineral Fiber Block and Board Thermal Insulation
<b>ASTM C518</b>	Standard Test Methods for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
<b>ASTM C356</b>	Standard Test Method for Linear Shrinkage of Preformed High-Temperature Thermal Insulation Subjected to Soaking Heat
<b>CAN/ULC-S114</b>	Standard Method of Test for Determination of Non-combustibility in Building Materials
<b>ASTM E136</b>	Standard Test Method for Behavior of Materials in a Vertical Tube Furnace at 750°C
<b>CAN/ULC-S129</b>	Standard Method of Test for Smoulder Resistance of Insulation (Basket Method)
<b>CAN/ULC-S102</b>	Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies
<b>ASTM E84</b>	Standard Test Method for Surface Burning Characteristics of Building Materials
<b>ASTM E2307</b>	Standard Test Method for Determining Fire Resistance of Perimeter Fire Barriers Using Intermediate-Scale, Multi-story Test Apparatus
<b>ASTM C1104</b>	Standard Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation
<b>ASTM E96</b>	Standard Test Methods for Water Vapor Transmission of Materials
<b>ASTM C1338</b>	Standard Test Method for Determining Fungi Resistance of Insulation Materials and Facings
<b>ASTM C795</b>	Standard Specification for Thermal Insulation for Use in Contact with Austenitic Stainless Steel



# Thermafiber® FireSpan™ 40 & 90 Mineral Wool Fire Containment Insulation

## Performance Criteria

<b>Compliance</b>	Evaluation Listing No. 14060-L Type I (Unfaced), Type III (Foil Face) Type I, III (Class A, Category 1) Type IA, IB, II, III, IVA	CCMC CAN/ULC-S702 ASTM C665 ASTM C612
<b>Density</b>	FireSpan™ 40      64 kg/m <sup>3</sup> (4.0 lbs/ft <sup>3</sup> ) FireSpan™ 90      128 kg/m <sup>3</sup> (8.0 lbs/ft <sup>3</sup> )	Nominal
<b>Thermal</b>	RSI value/25.4 mm @ 24 °C    0.74 m <sup>2</sup> •K/W R-value/inch @ 75 °F          4.2 hr•ft <sup>2</sup> •°F/Btu	ASTM C518
<b>Stability</b>	Linear Shrinkage <2% @ 650°C (1200°F)	ASTM C356
<b>Fire</b>	Non-Combustible Non-Combustible Smoulder Resistance Mean Mass Loss ≤ 0.02% Flame Spread 0; Smoke Developed 0 Flame Spread 0; Smoke Developed 0 Perimeter Fire Containment (see UL & Intertek listings)	CAN/ULC-S114 ASTM E136 CAN/ULC S-129 CAN/ULC-S102 ASTM E84 ASTM E2307
<b>Moisture</b>	Moisture Absorption < 1% by volume Water Vapour Transmission; Unfaced    2850 ng/Pa.s.m <sup>2</sup> (50 Perms) Foil Faced  1 ng/Pa.s.m <sup>2</sup> (0.02 Perms) Fungi Resistance - Pass	ASTM C1104 ASTM E96 ASTM C1338
<b>Corrosion</b>	Austenitic Steel - Non-corrosive Steel, Aluminum & Copper - Non-corrosive	ASTM C795 ASTM C665

## Sizes

Product	Thickness <sup>†</sup>	Widths	Lengths
FireSpan™ 40	51 mm (2") - 179 mm (7")	610 mm (24") 914 mm (36") 1829 mm (72")	1219 mm (48") 1524 mm (60") 1829 mm (72")
FireSpan™ 90	25 mm (1") - 179 mm (7")		

<sup>†</sup>Available in 12.7 mm (1/2") increments



## Quality Statement, Tests, Certifications, and Approvals

- Fire resistance verified by ULC, UL and Intertek.
- Perimeter Fire Containment Systems verified by testing to ASTM E2307. For complete information see UL and Intertek directories.
- Recycled content verified by ICC-ES.

## Delivery and Storage

Deliver products in their original packages, and store in enclosed shelter.

## Limitations

Packaging is not UV resistant. Shelter unused packages from the elements.

## Safety

Contact with mineral wool may cause temporary eye and skin irritation. Wear eye protection and long-sleeved loose fitting clothing closed at the neck and wrists. For additional information refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

## Availability/Cost

Contact Owens Corning local Area Sales Manager. See ASM territory map via [www.thermafiber.ca/contact](http://www.thermafiber.ca/contact).

## PRODUCT PROPERTIES

### Materials

Mineral wool, Type I & III (to CAN/ULC S702), non-combustible (to CAN/ULC-S114), non-corrosive (to ASTM C665).



# Thermafiber® FireSpan™ 40 & 90 Mineral Wool Fire Containment Insulation

## PRODUCT PLACEMENT

### Installation

- Install according to assembly listing in UL and Intertek directories.
- Mechanically attach to horizontal and vertical aluminum framing with approved insulation fasteners.
- Thermafiber Inc.'s patented Impasse® system is designed to quickly and easily attach FireSpan™ to curtain wall systems.
- Reinforce insulation on the outer insulation surface at the safing line; typical reinforcement members include hat channels, “L” angles, and “T” bars.
- Protect exposed vertical aluminum mullions with Firespan™ 90 mullion covers.
- Interior joint between floor assembly and exterior curtain wall to be compression fit with Thermafiber® Safing insulation.
- Cut insulation with a serrated knife.

### Technical Services Available

For Canadian Thermafiber® Technical inquiries please contact Matthew Schiedel: [matthew.schiedel@owenscorning.com](mailto:matthew.schiedel@owenscorning.com) or at 1-844-304-1623



Current Ed: 2018-09-01  
Previous Ed: 2017-05-01

### Disclaimer of Liability

Thermafiber, Inc. shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than the intended use. Thermafiber, Inc. liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing within thirty (30) days from date it was or reasonably should have been discovered.

LEED® is a registered trademark of the U.S. Green Building Council.  
Green Globes® is a registered trademark of Green Building Initiative, Inc.



**THERMAFIBER, INC.**  
ONE OWENS CORNING PARKWAY  
TOLEDO, OHIO, USA 43659  
**1-800-GET-PINK®**  
[www.thermafiber.ca](http://www.thermafiber.ca)

Pub. No. 600006A Printed in Canada. September 2018.  
THE PINK PANTHER™ & © 1964–2018 Metro-Goldwyn-Mayer Studios Inc.  
All Rights Reserved. The colour PINK is a registered trademark of Owens Corning.  
© 2018 Owens Corning. All Rights Reserved. © 2018 Thermafiber, Inc.  
All Rights Reserved.

