



Thermafiber® VersaBoard™

Mineral Wool Multipurpose Insulation

PRODUCT FEATURES

Description

Mineral wool multipurpose thermal insulation with fire resistive, acoustic and energy conserving properties; available with a variety of facing options suitable for commercial construction applications.

Basic Uses/Related Uses

Thermal, fire resistive and acoustical insulation for various commercial construction assemblies. Available with various facing options, VersaBoard™ insulation is perfectly suitable for parking garages, under decking, mechanical rooms and other areas where insulation is required. VersaBoard™ 60 can be used as a thermal barrier for foamed plastics, certified to CAN/ULC-S124.

Selection Criteria

- Non-combustible
- Moisture resistant and non-deteriorating
- Non-corrosive
- Vermin resistant
- Helps conserve energy, reduce greenhouse gas emissions
- Fire resistant to temperatures above 1,093° C (2,000° F)
- Enhances acoustical and thermal performance

Sustainability Criteria

- Recycled content minimum 70%, standard fiber
- Bronze Material Health Certificate from Cradle to Cradle
- Contributes to credits in several green building programs such as LEED® and Green Globes®
- For more information see Environmental Product Declaration (EPD) certified by UL Environment via www.thermafiber.ca/sustainability

Applicable Standards

CAN/ULC-S702	Standard for Mineral Fibre Thermal Insulation for Buildings
ASTM C665	Standard Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing
ASTM C612	Standard Specification for Mineral Fiber Block and Board Thermal Insulation
ASTM C518	Standard Test Methods for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
ASTM C356	Standard Test Method for Linear Shrinkage of Preformed High-Temperature Thermal Insulation Subjected to Soaking Heat
CAN/ULC-S114	Standard Method of Test for Determination of Non-combustibility in Building Materials
ASTM E136	Standard Test Method for Behavior of Materials in a Vertical Tube Furnace at 750°C
CAN/ULC-S129	Standard Method of Test for Smoulder Resistance of Insulation (Basket Method)
CAN/ULC-S102	Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies
ASTM E84	Standard Test Method for Surface Burning Characteristics of Building Materials
CAN/ULC-S124	Standard Method of Test for the Evaluation of Protective Coverings for Foamed Plastic
ASTM C1104	Standard Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation
ASTM E96	Standard Test Methods for Water Vapor Transmission of Materials
ASTM C1338	Standard Test Method for Determining Fungi Resistance of Insulation Materials and Facings
ASTM C795	Standard Specification for Thermal Insulation for Use in Contact with Austenitic Stainless Steel
ASTM C423	Standard Test Method for Sound Absorption Coefficients by the Reverberation Room Method






Thermafiber® VersaBoard™

Mineral Wool Multipurpose Insulation

Performance Criteria

Compliance	Evaluation Listing No. 14060-L	CCMC	
	Type I (Unfaced), Type III (Foil Face)	CAN/ULC-S702	
	Type I (Unfaced), Type II (Black & White Mat, ASJ), Type III (Foil Face)	ASTM C665	
	VersaBoard™ 35 - Type IA	ASTM C612	
	VersaBoard™ 40, 60 & 80 - Type IA, IB, II, III, IVA		
Density	VersaBoard™ 35	56 kg/m ³ (3.5 lbs/ft ³)	Actual
	VersaBoard™ 40	64 kg/m ³ (4.0 lbs/ft ³)	
	VersaBoard™ 60	96 kg/m ³ (6.0 lbs/ft ³)	
	VersaBoard™ 80	128 kg/m ³ (8.0 lbs/ft ³)	
Thermal	VersaBoard™ 35		ASTM C518
	RSI value/25.4 mm @ 24 °C	0.71 m ² ·K/W	
	R-value/inch @ 75 °F	4.0 hr·ft ² ·°F/Btu	
	VersaBoard™ 40 & 60		
RSI value / 25.4 mm @ 24 °C	0.74 m ² ·K/W		
R-value / inch @ 75 °F	4.2 hr·ft ² ·°F/Btu		
VersaBoard™ 80			
RSI value / 25.4 mm @ 24 °C	0.72 m ² ·K/W		
R-value / inch @ 75 °F	4.1 hr·ft ² ·°F/Btu		
Stability	Linear Shrinkage <2% @ 650°C (1200°F)	ASTM C356	
Fire	Non-Combustible	CAN/ULC-S114	
	Non-Combustible	ASTM E136	
	Smoulder Resistance Mean Mass Loss ≤ 0.02%	CAN/ULC-S129	
	Flame Spread 0; Smoke Developed 0	CAN/ULC-S102	
	Flame Spread 0; Smoke Developed 0	ASTM E84	
	VersaBoard™ 60 Class A - min. 76 mm (3") thickness Class B - min. 51 mm (2") thickness QAI Listing No. B1079	CAN/ULC-S124	
Moisture	Moisture Absorption < 1% by volume	ASTM C1104	
	Water Vapour Transmission; Unfaced 2850 ng/Pa.s.m ² (50 Perms) Foil Faced 1 ng/Pa.s.m ² (0.02 Perms)	ASTM E96	
	Fungi Resistance - Pass	ASTM C1338	
Corrosion	Austenitic Steel - Non-corrosive	ASTM C795	
	Steel, Aluminum & Copper - Non-corrosive	ASTM C665	
Acoustic	Contact Technical Services for Test Data	ASTM C423	



Sizes

Product	Thickness [†]	Widths	Lengths
VersaBoard™ 35	38 mm (1-1/2") - 179 mm (7")	610 mm (24") 914 mm (36")	1219 mm (48") 1524 mm (60")
VersaBoard™ 40, 60	25 mm (1") - 179 mm (7")		
VersaBoard™ 80	25 mm (1") - 127 mm (5")		

[†]Available in 12.7 mm (1/2") increments

Facing Options

VersaBoard™ insulation can be manufactured with various facings including Foil facing, All Service Jacket (ASJ) facing, Black and White fiberglass mat facings.

Product	Foil Facing	Other Facings*
VersaBoard™ 35	≥ 64 mm (2.5")	≥ 89 mm (3.5")
VersaBoard™ 40	≥ 51 mm (2.0")	≥ 76 mm (3.0")
VersaBoard™ 60	≥ 38 mm (1.5")	≥ 51 mm (2.0")
VersaBoard™ 80	≥ 25 mm (1.0")	≥ 38 mm (1.5")

*Felt exposure may occur on the edges of material with various facings. All edges must be taped if material experiences exposed edges.

Quality Statement, Tests, Certifications and Approvals

- Fire resistance verified by QAI - QAI Listing No. B1079-1.
- Recycled content verified by ICC-ES.

Delivery and Storage

Deliver products in their original packages, and store in enclosed shelter.

Limitations

VersaBoard™ insulation is not listed by ULC, UL or Intertek for use in fire rated systems. Refer to referenced product in appropriate listings for fire rated systems. Packaging is not UV resistant. Shelter unused packages from the elements.





Thermafiber® VersaBoard™

Mineral Wool Multipurpose Insulation

Safety

Contact with mineral wool may cause temporary eye and skin irritation. Wear eye protection and long-sleeved loose fitting clothing closed at the neck and wrists. For additional information refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

Availability/Cost

Contact Owens Corning local Area Sales Manager. See ASM territory map via www.thermafiber.ca/contact.

PRODUCT PROPERTIES

Materials

Mineral wool, Type I & III (to CAN/ULC-S702), non-combustible (to CAN/ULC-S114), non-corrosive (to ASM C665).

PRODUCT PLACEMENT

Installation

Thermafiber Inc. recommends mechanical attachment of Thermafiber® VersaBoard™ products. Standard insulation pins and washers are recommended.

Technical Services Available

For Canadian Thermafiber® Technical inquiries please contact Matthew Schiedel: matthew.schiedel@owenscorning.com or at 1-844-304-1623



Current Ed: 2018-09-01
Previous Ed: 2017-05-01



Disclaimer of Liability

Thermafiber, Inc. shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than the intended use. Thermafiber, Inc. liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing within thirty (30) days from date it was or reasonably should have been discovered.

LEED® is a registered trademark of the U.S. Green Building Council.
Green Globes® is a registered trademark of Green Building Initiative, Inc.

THERMAFIBER, INC.
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO, USA 43659
1-800-GET-PINK®
www.thermafiber.ca

Pub. No. 600012A Printed in Canada. September 2018.
THE PINK PANTHER™ & © 1964–2018 Metro-Goldwyn-Mayer Studios Inc.
All Rights Reserved. The colour PINK is a registered trademark of Owens Corning.
© 2018 Owens Corning. All Rights Reserved. © 2018 Thermafiber, Inc.
All Rights Reserved.

